

# SABIC® PP 500P

POLYPROPYLENE HOMOPOLYMER  
REGION ASIA

## DESCRIPTION

SABIC® PP 500P is a medium flow, multipurpose grade for extrusion and injection molding applications.

## TYPICAL APPLICATIONS

If applied for extrusion 500P shows an excellent stretch ability and is therefore suitable for tapes and strapping, high tenacity yarns and carpet backing. It can also be used in ropes and twines, woven bags, flexible intermediate bulk containers, geotextiles and concrete reinforcements.

For thermoforming it shows a unique balance between transparency, impact resistance and thickness uniformity.

500P is also suitable for production of injection molded articles e.g. caps and closures and house ware products, where this grade shows a high stiffness, combined with a fair impact resistance and very good surface hardness.

## TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate</b>			
at 230°C and 2.16kg	3	g/10 min	ASTM D1238
<b>Density</b>			
at 23°C	905	kg/m <sup>3</sup>	ASTM D638
<b>MECHANICAL PROPERTIES</b>			
<b>Flexural Modulus (1% Secant)</b>	1500	MPa	ASTM D790 A
<b>Izod Impact Strength</b>			
notched, at 23°C	25	J/m	ASTM D256
<b>Rockwell Hardness, R-Scale</b>	102	-	ASTM D785
<b>FILM PROPERTIES</b>			
<b>Tensile Properties <sup>(1)</sup></b>			
stress at yield	35	MPa	ASTM D638
strain at yield	10	%	ASTM D638
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>	152	°C	ASTM D1525
<b>Heat deflection temperature <sup>(2)</sup></b>			
at 455kPa	100	°C	ASTM D648



- (1) Based on injection molded specimens.
- (2) Flat wise ( testbar 80\*10\*4mm)

## PROCESSING CONDITIONS

Typical processing conditions for 500P are:

Barrel temperature range: 235 - 250°C

## HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

SABIC® PP 500P is suitable for food contact application. Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>. For additional specific information please contact SABIC local representative.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 ([www.ul.com](http://www.ul.com)).

## QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

## STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.