

# LL7610D1

Linear Low Density Polyethylene Resin

**Special Characteristics :** InnoPlus LL7610D1 is a linear low density polyethylene with hexene comonomer, with optimize slip and antiblock content for easy opening. InnoPlus LL7610D1 have been developed for blown film application by offering the excellent toughness and high mechanical strength with good bubble stability.

**Typical Applications :** InnoPlus LL7610D1 is recommended in blending formula for producing the general purpose films, liners, heavy duty films, food packaging and agricultural films.

**Additives :** Slip 700 ppm and Antiblock 700 ppm

**Typical Properties :**

Properties	LL7610D1	Unit	Test Method
<b>Physical Properties (Based on pellets and press-molded sheet)</b>			
Melt Flow Rate (190 °C, 2.16 kg)	1	g/10 min	ASTM D1238
Density	0.920	g/cm <sup>3</sup>	ASTM D792
Melting Temperature	121	°C	ASTM D3418
Vicat Softening Point	100	°C	ASTM D1525

## Film Properties\* (Based on blown film)

Tensile Strength at Break (MD/TD)	40 / 30	MPa	ASTM D882
Elongation at Break (MD/TD)	650 / 750	%	ASTM D882
Tensile Modulus, 1% Secant (MD/TD)	250 / 300	MPa	ASTM D882
Dart Impact Strength	180	g	ASTM D1709
Tear Strength (MD/TD)	350 / 500	g	ASTM D1922

\* Film made on blown film line at blow up ratio 2.5. Gloss (45°) obtained from 40 microns film while other film properties obtained from 25 microns film.

### Recommendation :

The recommended temperature setting is in the range of 160 – 180 °C for extruder and 170 – 190 °C for die zone.

### FDA Statement :

Food and Drug Administration US FDA 21 CFR 177.1520 and Commission Regulation (EU) 10/2011. More compliance regulations and standards that related to the product shall be exhibited in Product Regulatory Certificate (PRC) document.

**Disclaimer:** To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.